


Townsend Bearings



Adhesives, Sealants and Repair Compounds



Product	Strength	Size of Thread	Fuctional Strength (Typical @ 22°C)	Breakaway Torque M10	Long Term Temp. Resistance	Medium
Loctite 222	Low	Up to M36	6 Hrs	6 Nm	+150°C	Liquid
Loctite 243	Medium	Up to M36	2 Hrs	20 Nm	+150°C	Liquid
Loctite 248	Medium	Up to M50	6 Hrs	19 Nm	+150°C	Semi-Solid
Loctite 268	High	Up to M50	24 Hrs	25 Nm	+150°C	Semi-Solid
Loctite 2701	High	Up to M20	6 Hrs	38 Nm	+150°C	Liquid
Loctite 290	Med/High	Up to M6	3 Hrs	10 Nm	+150°C	Liquid
Dunlop SAS 116	Medium	-	20 min	12-17 Nm	-50°C - 150°C	Liquid